




Exceptional strength & durability
Dimensional stability

602N **602N Opaque**

■ **Technical properties**

Standards

Yarn	1100 dtex PES HT	1100 dtex PES HT	TERSUISSE 
Finish	Varnish both sides	Varnish both sides	
Weight	18.3 oz/yd ²	22 oz/yd ²	EN ISO 2286-2
Width	105.1 in	61 in / 98.4 in / 105.1 in	
Standard length	54.6 yds	61 in: 109.3 yds 98.4 & 105.1 in: 273.4 yds	
Tensile strength (warp/weft)	230/220 daN/5 cm	230/220 daN/5 cm	EN ISO 1421
Tear strength (warp/weft)	20/20 daN	20/20 daN	DIN 53.363
Elongation under load (warp/weft)	< 1% / <1%	< 1% / <1%	NF EN 15619
Flame retardancy	Method 2/ NFPA 701 • CSFM T19 B1/ DIN 4102-1 • M2/ NFP 92-507	Method 1 & 2/ NFPA 701 • CSFM T19 B1/ DIN 4102-1 • M2/ NFP 92-507	
Cold resistance / heat resistance	-22°F / +158°F	-22°F / +158°F	EN ISO 4675

■ **Certifications, labels, warranties**




Preconstraint[®]
technology

Translucent



602N-8100



602N-8341



602N-8861



602N-1071



602N-1070



602N-1060



602N-1065



602N-1055



602N-1051




602N-1075

Opaque



602N-8503 / 8103



602N-50020

The colors and textures represented in this document are provided as a reference only. Whether viewed on screen or printed, they cannot accurately match the real colors and textures and are therefore not contractual. The technical data above are average values with a +/- 5% tolerance. The buyer of our products is fully responsible for their application or their transformation concerning any possible third party. The buyer of our products is responsible for their implementation and installation according to the standards, use and customs and safety rules of the countries where they are used. For information on our contractual warranty, please refer to the relevant terms and conditions. The values quoted above represent results of tests performed in compliance with common design practices and are provided for information only to enable customers to make the best use of our products. Our products are subjects to evolutions due to technical progress, we remain entitled to modify the characteristics of our products at any time. The buyer of our products is responsible for checking the validity of the above data.