



E Screen 10%

Specifications

Product Category: Conventional	Composition: 36% Fiberglass / 64% Vinyl
Openness Factor: 10%	Standard Packaging: Rolls of 30 ly (27 lm)
UV Blockage: Approximately 90%	Width: 78" (200 cm), 98" (250 cm), 122" (310 cm)
Fabric Style: Basketweave	Weight: 10.3 oz / yd ² (350 g / m ²) ± 5%
Item #: 7510	Thickness: .020" (0.52 mm) ± 5%

Glass Performance

Glass Type	Appearance	VLT (Tv)	SHGC (G-Value)
Common Glass Types	Clear	70	0.38

Common Glass Types: Guardian SN68, Viracon 1-2 M, PPG Solarban 60

Coating and Location: Low E on Surface #2

Construction: 6 mm / 1/2" air / 6 mm

Fabric Performance

Fabric + Glass Performance

Color#	Color Name	Ts	Rs	As	VLT (Tv)	SHGC (G-Value) Interior Fabric	% Improvement of SHGC with Fabric
02.02	White/White	25	66	9	22	0.28	26%
02.07	White/Pearl	20	50	30	18	0.31	18%
02.20	White/Linen	25	58	17	22	0.30	21%
20.20	Linen/Linen	27	47	26	23	0.31	18%
30.01	Charcoal/Grey	12	8	80	11	0.37	3%
30.30	Charcoal/Charcoal	12	3	85	12	0.37	3%
30.61	Charcoal/Cocoa	11	5	84	11	0.37	3%
30.71	Charcoal/Apricot	14	14	72	13	0.36	5%
61.61	Cocoa/Cocoa	11	7	82	11	0.37	3%
61.71	Cocoa/Apricot	14	16	70	13	0.35	8%

The performance tests were conducted in accordance with EN 14501:2005, ASTM E891, ASTM E903-96: Solar Heat Gain Coefficient SHGC (G-Value), Solar Transmittance (Ts), Solar Reflectance (Rs), Solar Absorptance (As), Visible Light Transmission VLT (Tv), Double Glazing 6 mm / 1/2" air / 6 mm with low E on surface #2. Glass performance tests were conducted using the Lawrence Berkeley National Laboratory Window 6.3 NFRC certified software. For up-to-date test results, performance specifications and larger samples, contact the Mermet Technical Department at: www.mermetusa.com

Fabrication Methods:

Cutting: cold, ultrasonic or crush
 Welding: radio frequency, high frequency, impulse, hot air, wedge

Fire Classifications:

NFPA 701-10 TM#1, California U.S. Title 19
 CAN/ULC-S109-03 Small Flame Test

Environmental Benefits:

RoHS - Lead Free

Bacterial and Fungal Resistance:

ASTM E2180, ASTM G21

We recommend testing all cutting and welding methods prior to use to confirm they meet your individual fabrication specifications.

Care & Handling

Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent. Rinse with clean water. Leave the blind down until completely dry. You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

5970 N. Main Street • Cowpens, SC 29330

Sales Department: Ph (866) 902-9647

info@mermetusa.com