

TEXTILENE[®] nano[™]97 Twill is a durable, two-sided, synthetic fabric. It is lighter and finer with the same technical qualities as the original TEXTILENE[®]. TEXTILENE[®] nano[™]97 Twill is excellent for exterior use and can reduce energy costs while blocking up to 97% of the sun's harmful rays.



*Custom colors and widths available. Minimum order of 1000 yards. Upcharges may apply.

4031 Ross Clark Circle NW • Dothan, Alabama 36303 • 1.800.633.7550 • Fax: 334.673.4126 www.twitchellcorp.com

Specifications



REACH Compliant: Regulated by Registration, Evaluation, Authorization and Restriction of Chemicals. REACH places greater responsibility on industry to manage the risks that chemicals may pose to human health and the environment


Children's Toy Act: Does not contain harmful phthalates listed under Section 108 of the Consumer Product Safety Improvement Act of 2008 (CPSIA).

Fire Classification: Passes California U.S. Title 19 (small scale), NFPA701-2004 TM#1 (small scale), NFPA 101 (Class A Rating), UBC (Class 1), BS 5867 2008 Part 2 Type B Performance, NFPA 701 TM #2 (large scale), and CAN/ULC-S 109-03 (large and small scale).

Environmental Certification: GREENGUARD gold certified. Acceptable for use in environments such as schools and healthcare facilities. Complies with requirements of the State of California's Department of Public Health "Standard Method for Testing and Evaluation of Volatile Organic Chemical Emissions from Indoor Sources Using Environmental Chambers, Version 1.1 (2010)" (also known as California Section 01350).

RoHS Compliant : Free of Lead (Pb), Cadmium (Cd), Mercury (Hg), Hexavalent chromium (Hex-Cr), Polybrominated biphenyls (PBB), and Polybrominated diphenyl ethers (PBDE).

Bacteria and Fungal Resistance: Passes ASTM E 2180, ASTM G22, AATCC30 Part 3, ASTM G21, ASTM D 3273. Includes specially formulated antimicrobial.





Technical Data

Item Number: T18FVS, T18FVT

Product Description: A woven fabric using .014" diameter vinyl coated 420 denier polyester core yarns in the warp and fill.

oute	ASTM	Warp	Fill	Typical					
nch	D3775-12	34.0 ±0.5	35.5 ±0.5						
	D3776-09			14.6					
	D3776-09			495.0					
rab), lbf / daN	D5034-09	499.5 / 222.2	367.8 / 163.6						
trip), lbf / daN	D5035-11	192.6 / 85.7	197.5 / 87.9						
ezoidal), lbf / daN	D5733	58.0 / 25.8	52.3 / 23.3						
	D5035-11	10.6	13.8						
Ce led weight)	D3884-09	No Exposure of Core Yarn							
g		CA Title 19 & NFPA 701							
0 hours	G154	Trace Discoloration							
	G21-13	No Growth							
mm	D1777-96			0.0308 / 0.7823					


The above results are a representation of real data from single test samples. Presently no specification is

Solar Heat Control Properties for Twitchell Technical Products, LLC Shade Fabric Interior Use at 0 Degree Profile Angle

									SC (Single Glass)		
Color	Ts	Rs	As	Τv	Rv	Av	Tuv	0-F	1/8" CI.	1/4" CI.	1/4" H.A.
Charcoal	6	6	88	8	5	87	5	4	0.73	0.69	0.50







4031 Ross Clark Circle NW • Dothan, Alabama 36303 • 1.800.633.7550 • Fax: 334.673.4126 www.twitchellcorp.com